

2.1 Load tables for walls constructed with 15MPa blocks:

The tables in this section are for walls where the design is based on either the height or the length of the wall. Refer to page 4 of Section 2 above to determine if wall height or wall length governs the design of the wall.

Alternatively for the wall under consideration, determine the maximum design load based on height and the maximum design load based on length using the charts below, and adopt the larger of the two values.

15MPa Blocks, Minimum C25/30 Grout *

* Note: For further guidance on grout refer Part 1 Section 5 of this Design Manual. C25/30 is the minimum grout strength for reinforced masonry.

Tables: (Unchamfered blocks)

| | |
|--------------------------|---|
| Table UH200-15-1: | 15MPa blocks, $a_v = 0.75$, height governs |
| Table UH200-15-2: | 15MPa blocks, $a_v = 1.0$, height governs |
| Table UL200-15-1: | 15MPa blocks, $a_h = 0.75$, length governs |
| Table UL200-15-2: | 15MPa blocks, $a_h = 1.0$, length governs |
| Table UL200-15-3: | 15MPa blocks, $a_h = 2.0$, length governs |
| Table UL200-15-4: | 15MPa blocks, $a_h = 2.5$, length governs |

Table UH200-15-1

| 200 MORTARLESS WALL (UNCHAMFERED) | | | | | | | | | | | | | | |
|--|---------------------------|------------------|---|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|
| Block: 15 MPa | | | Wall Span: VERTICAL | | | | | | | | $a_v = 0.75$ | | | |
| Grout: C25/30 | | | Category 1 masonry units (refer BS 5628-1 Clause 3.3) | | | | | | | | | | | |
| MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
| Wall height H (mm) | $h_{ef} = 0.75 H$ (mm) | $S_r = h_{ef}/t$ | $e_x = 8.7\text{mm}$ | | $e_x = 10\text{mm}$ | | $e_x = 20\text{mm}$ | | $e_x = 30\text{mm}$ | | $e_x = 40\text{mm}$ | | $e_x = 50\text{mm}$ | |
| | | | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) |
| 1600 | 1200 | 6 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2000 | 1500 | 7.5 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2400 | 1800 | 9 | 1.00 | 405 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2800 | 2100 | 10.5 | 0.97 | 394 | 0.97 | 390 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 3200 | 2400 | 12 | 0.94 | 381 | 0.94 | 378 | 0.87 | 351 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 3600 | 2700 | 13.5 | 0.91 | 367 | 0.90 | 364 | 0.83 | 337 | 0.77 | 310 | 0.66 | 267 | 0.55 | 222 |
| 4000 | 3000 | 15 | 0.87 | 351 | 0.86 | 348 | 0.79 | 321 | 0.73 | 295 | 0.66 | 267 | 0.55 | 222 |
| 4400 | 3300 | 16.5 | 0.83 | 334 | 0.82 | 330 | 0.75 | 304 | 0.69 | 277 | 0.62 | 250 | 0.55 | 222 |
| 4800 | 3600 | 18 | 0.78 | 315 | 0.77 | 311 | 0.70 | 285 | 0.64 | 258 | 0.57 | 231 | 0.51 | 204 |
| 5200 | 3900 | 19.5 | 0.73 | 294 | 0.72 | 290 | 0.65 | 264 | 0.59 | 237 | 0.52 | 210 | 0.45 | 184 |
| 5600 | 4200 | 21 | 0.67 | 271 | 0.66 | 268 | 0.60 | 241 | 0.53 | 214 | 0.46 | 188 | 0.40 | 161 |
| 6000 | 4500 | 22.5 | 0.61 | 247 | 0.60 | 244 | 0.54 | 217 | 0.47 | 190 | 0.40 | 164 | 0.34 | 137 |
| 6400 | 4800 | 24 | 0.55 | 221 | 0.54 | 218 | 0.47 | 191 | 0.41 | 164 | 0.34 | 138 | 0.28 | 111 |
| 6800 | 5100 | 25.5 | 0.48 | 194 | 0.47 | 190 | 0.40 | 164 | 0.34 | 137 | 0.27 | 110 | 0.21 | 84 |
| 7200 | 5400 | 27 | 0.41 | 165 | 0.40 | 161 | 0.33 | 134 | 0.27 | 108 | 0.20 | 81 | 0.13 | 54 |
| | | | $e_x/t_b = 0.05$ | | | | | | | | | | $e_x/t_b = 0.29$ | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_v is the effective height multiplier. $a_v = 0.75$ applies to walls that have enhanced resistance to lateral movement top and bottom, e.g. walls built off concrete slabs or footings at the bottom and supporting slabs at the top.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table H200-15-2

200 MORTARLESS WALL (UNCHAMFERED)

Block: 15
MPa
Grout: C25/30

Wall Span: VERTICAL

$a_v = 1.0$

Category 1 masonry units (refer BS 5628-1 Clause 3.3)

| MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
|--|----------------------|------------------|----------------------|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|---------------------|-----------------|
| Wall height H (mm) | $h_{ef} = H$ (mm) | $S_r = h_{ef}/t$ | $e_x = 8.7\text{mm}$ | | $e_x = 10\text{mm}$ | | $e_x = 20\text{mm}$ | | $e_x = 30\text{mm}$ | | $e_x = 40\text{mm}$ | | $e_x = 50\text{mm}$ | |
| | | | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) | β | N_d (kN/m) |
| 1200 | 1200 | 6 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1600 | 1600 | 8 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2000 | 2000 | 10 | 0.98 | 398 | 0.98 | 394 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2400 | 2400 | 12 | 0.94 | 381 | 0.94 | 378 | 0.87 | 351 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2800 | 2800 | 14 | 0.90 | 362 | 0.89 | 359 | 0.82 | 332 | 0.76 | 305 | 0.66 | 267 | 0.55 | 222 |
| 3200 | 3200 | 16 | 0.84 | 340 | 0.83 | 336 | 0.77 | 310 | 0.70 | 283 | 0.63 | 256 | 0.55 | 222 |
| 3600 | 3600 | 18 | 0.78 | 315 | 0.77 | 311 | 0.70 | 285 | 0.64 | 258 | 0.57 | 231 | 0.51 | 204 |
| 4000 | 4000 | 20 | 0.71 | 286 | 0.70 | 283 | 0.63 | 256 | 0.57 | 230 | 0.50 | 203 | 0.44 | 176 |
| 4400 | 4400 | 22 | 0.63 | 255 | 0.62 | 252 | 0.56 | 225 | 0.49 | 199 | 0.43 | 172 | 0.36 | 145 |
| 4800 | 4800 | 24 | 0.55 | 221 | 0.54 | 218 | 0.47 | 191 | 0.41 | 164 | 0.34 | 138 | 0.28 | 111 |
| 5200 | 5200 | 26 | 0.46 | 184 | 0.45 | 181 | 0.38 | 154 | 0.32 | 127 | 0.25 | 101 | 0.18 | 74 |
| 5400 | 5400 | 27 | 0.41 | 165 | 0.40 | 161 | 0.33 | 134 | 0.27 | 108 | 0.20 | 81 | 0.13 | 54 |
| | | | $e_x/t_b = 0.05$ | | | | | | | | | | $e_x/t_b = 0.29$ | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_v is the effective height multiplier. $a_v = 1.0$ applies to walls that have simple resistance to lateral movement top and bottom, e.g. walls restrained by timber framed floors or roofs top and bottom.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-15-1

| 200 MORTARLESS WALL (UNCHAMFERED) | | | | | | | | | | | | | | |
|--|----------------------------------|-------------------------------------|---|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|---------------------------------------|-----------------------|--------------------------|
| Block: 15 MPa | | | Wall Span: HORIZONTAL | | | | | | | | | a _h = 0.75 | | |
| Grout: C25/30 | | | Category 1 masonry units (refer BS 5628-1 Clause 3.3) | | | | | | | | | | | |
| MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
| Wall Length L (mm) | L _{ef} = 0.75 L (mm) | S _r = L _{ef} /t | e _x = 8.7mm | | e _x = 10mm | | e _x = 20mm | | e _x = 30mm | | e _x = 40mm | | e _x = 50mm | |
| | | | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) |
| 1200 | 900 | 4.5 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1600 | 1200 | 6 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2000 | 1500 | 7.5 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2400 | 1800 | 9 | 1.00 | 405 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2800 | 2100 | 10.5 | 0.97 | 394 | 0.97 | 390 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 3200 | 2400 | 12 | 0.94 | 381 | 0.94 | 378 | 0.87 | 351 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 3600 | 2700 | 13.5 | 0.91 | 367 | 0.90 | 364 | 0.83 | 337 | 0.77 | 310 | 0.66 | 267 | 0.55 | 222 |
| 4000 | 3000 | 15 | 0.87 | 351 | 0.86 | 348 | 0.79 | 321 | 0.73 | 295 | 0.66 | 267 | 0.55 | 222 |
| 4400 | 3300 | 16.5 | 0.83 | 334 | 0.82 | 330 | 0.75 | 304 | 0.69 | 277 | 0.62 | 250 | 0.55 | 222 |
| 4800 | 3600 | 18 | 0.78 | 315 | 0.77 | 311 | 0.70 | 285 | 0.64 | 258 | 0.57 | 231 | 0.51 | 204 |
| 5200 | 3900 | 19.5 | 0.73 | 294 | 0.72 | 290 | 0.65 | 264 | 0.59 | 237 | 0.52 | 210 | 0.45 | 184 |
| 5600 | 4200 | 21 | 0.67 | 271 | 0.66 | 268 | 0.60 | 241 | 0.53 | 214 | 0.46 | 188 | 0.40 | 161 |
| 6000 | 4500 | 22.5 | 0.61 | 247 | 0.60 | 244 | 0.54 | 217 | 0.47 | 190 | 0.40 | 164 | 0.34 | 137 |
| 6400 | 4800 | 24 | 0.55 | 221 | 0.54 | 218 | 0.47 | 191 | 0.41 | 164 | 0.34 | 138 | 0.28 | 111 |
| 6800 | 5100 | 25.5 | 0.48 | 194 | 0.47 | 190 | 0.40 | 164 | 0.34 | 137 | 0.27 | 110 | 0.21 | 84 |
| 7200 | 5400 | 27 | 0.41 | 165 | 0.40 | 161 | 0.33 | 134 | 0.27 | 108 | 0.20 | 81 | 0.13 | 54 |
| | | | e _x /t _b = 0.05 | | | | | | | | | e _x /t _b = 0.29 | | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 0.75$ applies to walls that have enhanced resistance to lateral movement both ends, e.g. walls restrained by fully bonded intersecting walls at both ends.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-15-2

| 200 MORTARLESS WALL (UNCHAMFERED) | | | | | | | | | | | | | | |
|--|------------------------------------|--|---|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|---------------------------------------|-----------------------|--------------------------|
| Block: 15 MPa | | | Wall Span: HORIZONTAL | | | | | | | | | a _h = 1.0 | | |
| Grout: C25/30 | | | Category 1 masonry units (refer BS 5628-1 Clause 3.3) | | | | | | | | | | | |
| MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
| Wall Length L (mm) | L _{ef} = 1.0 L (mm) | S _r = L _{ef} /t | e _x = 8.7mm | | e _x = 10mm | | e _x = 20mm | | e _x = 30mm | | e _x = 40mm | | e _x = 50mm | |
| | | | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) |
| 1200 | 1200 | 6 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1600 | 1600 | 8 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2000 | 2000 | 10 | 0.98 | 398 | 0.98 | 394 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2400 | 2400 | 12 | 0.94 | 381 | 0.94 | 378 | 0.87 | 351 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 2800 | 2800 | 14 | 0.90 | 362 | 0.89 | 359 | 0.82 | 332 | 0.76 | 305 | 0.66 | 267 | 0.55 | 222 |
| 3200 | 3200 | 16 | 0.84 | 340 | 0.83 | 336 | 0.77 | 310 | 0.70 | 283 | 0.63 | 256 | 0.55 | 222 |
| 3600 | 3600 | 18 | 0.78 | 315 | 0.77 | 311 | 0.70 | 285 | 0.64 | 258 | 0.57 | 231 | 0.51 | 204 |
| 4000 | 4000 | 20 | 0.71 | 286 | 0.70 | 283 | 0.63 | 256 | 0.57 | 230 | 0.50 | 203 | 0.44 | 176 |
| 4400 | 4400 | 22 | 0.63 | 255 | 0.62 | 252 | 0.56 | 225 | 0.49 | 199 | 0.43 | 172 | 0.36 | 145 |
| 4800 | 4800 | 24 | 0.55 | 221 | 0.54 | 218 | 0.47 | 191 | 0.41 | 164 | 0.34 | 138 | 0.28 | 111 |
| 5200 | 5200 | 26 | 0.46 | 184 | 0.45 | 181 | 0.38 | 154 | 0.32 | 127 | 0.25 | 101 | 0.18 | 74 |
| 5400 | 5400 | 27 | 0.41 | 165 | 0.40 | 161 | 0.33 | 134 | 0.27 | 108 | 0.20 | 81 | 0.13 | 54 |
| | | | e _x /t _b = 0.05 | | | | | | | | | e _x /t _b = 0.29 | | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 1.0$ applies to walls that have simple resistance to lateral movement both ends, e.g. walls restrained by timber framed intersecting walls at both ends.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-15-3

| 200 MORTARLESS WALL (UNCHAMFERED) | | | | | | | | | | | | | | |
|--|------------------------------------|--|---|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|---------------------------------------|-----------------------|--------------------------|
| Block: 15 MPa | | | Wall Span: HORIZONTAL | | | | | | | | | a _h = 2.0 | | |
| Grout: C25/30 | | | Category 1 masonry units (refer BS 5628-1 Clause 3.3) | | | | | | | | | | | |
| MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
| Wall Length L (mm) | L _{ef} = 2.0 L (mm) | S _r = L _{ef} /t | e _x = 8.7mm | | e _x = 10mm | | e _x = 20mm | | e _x = 30mm | | e _x = 40mm | | e _x = 50mm | |
| | | | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) |
| 600 | 1200 | 6 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 800 | 1600 | 8 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1000 | 2000 | 10 | 0.98 | 398 | 0.98 | 394 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1200 | 2400 | 12 | 0.94 | 381 | 0.94 | 378 | 0.87 | 351 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1400 | 2800 | 14 | 0.90 | 362 | 0.89 | 359 | 0.82 | 332 | 0.76 | 305 | 0.66 | 267 | 0.55 | 222 |
| 1600 | 3200 | 16 | 0.84 | 340 | 0.83 | 336 | 0.77 | 310 | 0.70 | 283 | 0.63 | 256 | 0.55 | 222 |
| 1800 | 3600 | 18 | 0.78 | 315 | 0.77 | 311 | 0.70 | 285 | 0.64 | 258 | 0.57 | 231 | 0.51 | 204 |
| 2000 | 4000 | 20 | 0.71 | 286 | 0.70 | 283 | 0.63 | 256 | 0.57 | 230 | 0.50 | 203 | 0.44 | 176 |
| 2200 | 4400 | 22 | 0.63 | 255 | 0.62 | 252 | 0.56 | 225 | 0.49 | 199 | 0.43 | 172 | 0.36 | 145 |
| 2400 | 4800 | 24 | 0.55 | 221 | 0.54 | 218 | 0.47 | 191 | 0.41 | 164 | 0.34 | 138 | 0.28 | 111 |
| 2600 | 5200 | 26 | 0.46 | 184 | 0.45 | 181 | 0.38 | 154 | 0.32 | 127 | 0.25 | 101 | 0.18 | 74 |
| 2700 | 5400 | 27 | 0.41 | 165 | 0.40 | 161 | 0.33 | 134 | 0.27 | 108 | 0.20 | 81 | 0.13 | 54 |
| | | | e _x /t _b = 0.05 | | | | | | | | | e _x /t _b = 0.29 | | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 2.0$ applies to walls that have enhanced resistance to lateral movement at one end that have a free edge at the other end.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-15-4

| 200 MORTARLESS WALL (UNCHAMFERED) | | | | | | | | | | | | | | |
|--|------------------------------------|--|--|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|-----------------------|--------------------------|---------------------------------------|--------------------------|-----------------------|--------------------------|
| Block: 15 MPa Grout: C25/30 | | | Wall Span: HORIZONTAL Category 1 masonry units (refer BS 5628-1 Clause 3.3) | | | | | | | | a _h = 2.5 | | | |
| MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES | | | | | | | | | | | | | | |
| Wall Length L (mm) | L _{ef} = 2.5 L (mm) | S _r = L _{ef} /t | e _x = 8.7mm | | e _x = 10mm | | e _x = 20mm | | e _x = 30mm | | e _x = 40mm | | e _x = 50mm | |
| | | | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) | β | N _d (kN/m) |
| 600 | 1500 | 7.5 | 1.00 | 404 | 0.99 | 400 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 800 | 2000 | 10 | 0.98 | 398 | 0.98 | 394 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1000 | 2500 | 12.5 | 0.93 | 377 | 0.92 | 373 | 0.88 | 356 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1200 | 3000 | 15 | 0.87 | 351 | 0.86 | 348 | 0.79 | 321 | 0.77 | 311 | 0.66 | 267 | 0.55 | 222 |
| 1400 | 3500 | 17.5 | 0.79 | 321 | 0.79 | 318 | 0.72 | 291 | 0.65 | 264 | 0.59 | 238 | 0.52 | 211 |
| 1600 | 4000 | 20 | 0.71 | 286 | 0.70 | 283 | 0.63 | 256 | 0.57 | 230 | 0.50 | 203 | 0.44 | 176 |
| 1800 | 4500 | 22.5 | 0.61 | 247 | 0.60 | 244 | 0.54 | 217 | 0.47 | 190 | 0.40 | 164 | 0.34 | 137 |
| 2000 | 5000 | 25 | 0.50 | 203 | 0.49 | 200 | 0.43 | 173 | 0.36 | 146 | 0.30 | 120 | 0.23 | 93 |
| 2100 | 5250 | 26.25 | 0.44 | 179 | 0.44 | 176 | 0.37 | 149 | 0.30 | 123 | 0.24 | 96 | 0.17 | 69 |
| | | | e _x /t _b = 0.05 | | | | | | | | e _x /t _b = 0.29 | | | |

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 2.5$ applies to walls that have simple resistance to lateral movement at one end that have a free edge at the other end.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).