

2.2 Load tables for walls constructed with 20MPa blocks:

The tables in this section are for walls where the design is based on either the height or the length of the wall. Refer to page 4 of Section 2 above to determine if wall height or wall length governs the design of the wall.

Alternatively for the wall under consideration, determine the maximum design load based on height and the maximum design load based on length using the charts below, and adopt the larger of the two values.

20MPa Blocks, Minimum C25/30 Grout *

* Note: For further guidance on grout refer Part 1 Section 5 of this Design Manual. C25/30 is the minimum grout strength for reinforced masonry.

Tables: (Unchamfered blocks)

Table UH200-20-1: 20MPa blocks, $a_v = 0.75$, height governs

Table UH200-20-2: 20MPa blocks, $a_v = 1.00$, height governs

Table UL200-20-1: 20MPa blocks, $a_h = 0.75$, length governs

Table UL200-20-2: 20MPa blocks, $a_h = 1.0$, length governs

Table UL200-20-3: 20MPa blocks, $a_h = 2.0$, length governs

Table UL200-20-4: 20MPa blocks, $a_h = 2.5$, length governs

Table UH200-20-1**200 MORTARLESS WALL (UNCHAMFERED)****Block: 20 MPa**
Grout: C25/30**Wall Span: VERTICAL**
Category 1 masonry units (refer BS 5628-1 Clause 3.3) **$a_v = 0.75$**

MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES														
Wall height H (mm)	$h_{ef} = 0.75 H$ (mm)	$S_r = h_{ef}/t$	$e_x = 8.7\text{mm}$		$e_x = 10\text{mm}$		$e_x = 20\text{mm}$		$e_x = 30\text{mm}$		$e_x = 40\text{mm}$		$e_x = 50\text{mm}$	
			β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)
1600	1200	6	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2000	1500	7.5	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2400	1800	9	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2800	2100	10.5	0.97	487	0.97	483	0.88	440	0.77	385	0.66	330	0.55	275
3200	2400	12	0.94	471	0.94	467	0.87	434	0.77	385	0.66	330	0.55	275
3600	2700	13.5	0.91	454	0.90	450	0.83	417	0.77	384	0.66	330	0.55	275
4000	3000	15	0.87	434	0.86	430	0.79	397	0.73	364	0.66	330	0.55	275
4400	3300	16.5	0.83	413	0.82	408	0.75	375	0.69	342	0.62	309	0.55	275
4800	3600	18	0.78	389	0.77	385	0.70	352	0.64	319	0.57	286	0.51	253
5200	3900	19.5	0.73	363	0.72	359	0.65	326	0.59	293	0.52	260	0.45	227
5600	4200	21	0.67	335	0.66	331	0.60	298	0.53	265	0.46	232	0.40	199
6000	4500	22.5	0.61	305	0.60	301	0.54	268	0.47	235	0.40	202	0.34	169
6400	4800	24	0.55	274	0.54	269	0.47	236	0.41	203	0.34	170	0.28	137
6800	5100	25.5	0.48	240	0.47	235	0.40	202	0.34	169	0.27	136	0.21	103
7200	5400	27	0.41	203	0.40	199	0.33	166	0.27	133	0.20	100	0.13	67
			$e_x/t_b = 0.05$											
								$e_x/t_b = 0.29$						

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_v is the effective height multiplier. $a_v = 0.75$ applies to walls that have enhanced resistance to lateral movement top and bottom, e.g. walls built off concrete slabs or footings at the bottom and supporting slabs at the top.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UH200-20-2

200 MORTARLESS WALL (UNCHAMFERED)

Block: 20 MPa

Grout: C25/30

Wall Span: VERTICAL

Category 1 masonry units (refer BS 5628-1 Clause 3.3)

$a_v = 1.0$

MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES															
Wall height H (mm)	$h_{ef} = H$ (mm)	$S_r = h_{ef}/t$	$e_x = 8.7\text{mm}$		$e_x = 10\text{mm}$		$e_x = 20\text{mm}$		$e_x = 30\text{mm}$		$e_x = 40\text{mm}$		$e_x = 50\text{mm}$		
			β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	
1200	1200	6	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275	
1600	1600	8	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275	
2000	2000	10	0.98	492	0.98	487	0.88	440	0.77	385	0.66	330	0.55	275	
2400	2400	12	0.94	471	0.94	467	0.87	434	0.77	385	0.66	330	0.55	275	
2800	2800	14	0.90	448	0.89	443	0.82	410	0.76	377	0.66	330	0.55	275	
3200	3200	16	0.84	420	0.83	416	0.77	383	0.70	350	0.63	317	0.55	275	
3600	3600	18	0.78	389	0.77	385	0.70	352	0.64	319	0.57	286	0.51	253	
4000	4000	20	0.71	354	0.70	350	0.63	317	0.57	284	0.50	251	0.44	218	
4400	4400	22	0.63	316	0.62	311	0.56	278	0.49	245	0.43	212	0.36	180	
4800	4800	24	0.55	274	0.54	269	0.47	236	0.41	203	0.34	170	0.28	137	
5200	5200	26	0.46	228	0.45	223	0.38	190	0.32	158	0.25	125	0.18	92	
5400	5400	27	0.41	203	0.40	199	0.33	166	0.27	133	0.20	100	0.13	67	
			$e_x/t_b = 0.05$											$e_x/t_b = 0.29$	

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_v is the effective height multiplier. $a_v = 1.0$ applies to walls that have simple resistance to lateral movement top and bottom, e.g. walls restrained by timber framed floors or roofs top and bottom.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-20-1

200 MORTARLESS WALL (UNCHAMFERED)														
Block: 20 MPa			Wall Span: HORIZONTAL								a _h = 0.75			
Grout: C25/30			Category 1 masonry units (refer BS 5628-1 Clause 3.3)											
MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES														
Wall Length L (mm)	L _{ef} = 0.75 L (mm)	S _r = L _{ef} /t	e _x = 8.7mm		e _x = 10mm		e _x = 20mm		e _x = 30mm		e _x = 40mm		e _x = 50mm	
			β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)
1200	900	4.5	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
1600	1200	6	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2000	1500	7.5	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2400	1800	9	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2800	2100	10.5	0.97	487	0.97	483	0.88	440	0.77	385	0.66	330	0.55	275
3200	2400	12	0.94	471	0.94	467	0.87	434	0.77	385	0.66	330	0.55	275
3600	2700	13.5	0.91	454	0.90	450	0.83	417	0.77	384	0.66	330	0.55	275
4000	3000	15	0.87	434	0.86	430	0.79	397	0.73	364	0.66	330	0.55	275
4400	3300	16.5	0.83	413	0.82	408	0.75	375	0.69	342	0.62	309	0.55	275
4800	3600	18	0.78	389	0.77	385	0.70	352	0.64	319	0.57	286	0.51	253
5200	3900	19.5	0.73	363	0.72	359	0.65	326	0.59	293	0.52	260	0.45	227
5600	4200	21	0.67	335	0.66	331	0.60	298	0.53	265	0.46	232	0.40	199
6000	4500	22.5	0.61	305	0.60	301	0.54	268	0.47	235	0.40	202	0.34	169
6400	4800	24	0.55	274	0.54	269	0.47	236	0.41	203	0.34	170	0.28	137
6800	5100	25.5	0.48	240	0.47	235	0.40	202	0.34	169	0.27	136	0.21	103
7200	5400	27	0.41	203	0.40	199	0.33	166	0.27	133	0.20	100	0.13	67
			e _x /t _b = 0.05										e _x /t _b = 0.29	

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 0.75$ applies to walls that have enhanced resistance to lateral movement both ends, e.g. walls restrained by fully bonded intersecting walls at both ends.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-20-2

200 MORTARLESS WALL (UNCHAMFERED)														
Block: 20 MPa			Wall Span: HORIZONTAL								a _h = 1.0			
Grout: C25/30			Category 1 masonry units (refer BS 5628-1 Clause 3.3)											
MAXIMUM DESIGN LOAD IN COMPRESSION (N _d) WITH DIFFERENT ECCENTRICITIES														
Wall Length L (mm)	L _{ef} = 1.0 L (mm)	S _r = L _{ef} /t	e _x = 8.7mm		e _x = 10mm		e _x = 20mm		e _x = 30mm		e _x = 40mm		e _x = 50mm	
			β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)	β	N _d (kN/m)
1200	1200	6	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
1600	1600	8	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
2000	2000	10	0.98	492	0.98	487	0.88	440	0.77	385	0.66	330	0.55	275
2400	2400	12	0.94	471	0.94	467	0.87	434	0.77	385	0.66	330	0.55	275
2800	2800	14	0.90	448	0.89	443	0.82	410	0.76	377	0.66	330	0.55	275
3200	3200	16	0.84	420	0.83	416	0.77	383	0.70	350	0.63	317	0.55	275
3600	3600	18	0.78	389	0.77	385	0.70	352	0.64	319	0.57	286	0.51	253
4000	4000	20	0.71	354	0.70	350	0.63	317	0.57	284	0.50	251	0.44	218
4400	4400	22	0.63	316	0.62	311	0.56	278	0.49	245	0.43	212	0.36	180
4800	4800	24	0.55	274	0.54	269	0.47	236	0.41	203	0.34	170	0.28	137
5200	5200	26	0.46	228	0.45	223	0.38	190	0.32	158	0.25	125	0.18	92
5400	5400	27	0.41	203	0.40	199	0.33	166	0.27	133	0.20	100	0.13	67
			e _x /t _b = 0.05										e _x /t _b = 0.29	

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 1.0$ applies to walls that have simple resistance to lateral movement both ends, e.g. walls restrained by timber framed intersecting walls at both ends.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-20-3

200 MORTARLESS WALL (UNCHAMFERED)

Block: 20 MPa
Grout: C25/30

Wall Span: HORIZONTAL
Category 1 masonry units (refer BS 5628-1 Clause 3.3)

$a_h = 2.0$

MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES														
Wall Length L (mm)	$L_{ef} = 2.0 L$ (mm)	$S_r = L_{ef}/t$	$e_x = 8.7\text{mm}$		$e_x = 10\text{mm}$		$e_x = 20\text{mm}$		$e_x = 30\text{mm}$		$e_x = 40\text{mm}$		$e_x = 50\text{mm}$	
			β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)
600	1200	6	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
800	1600	8	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
1000	2000	10	0.98	492	0.98	487	0.88	440	0.77	385	0.66	330	0.55	275
1200	2400	12	0.94	471	0.94	467	0.87	434	0.77	385	0.66	330	0.55	275
1400	2800	14	0.90	448	0.89	443	0.82	410	0.76	377	0.66	330	0.55	275
1600	3200	16	0.84	420	0.83	416	0.77	383	0.70	350	0.63	317	0.55	275
1800	3600	18	0.78	389	0.77	385	0.70	352	0.64	319	0.57	286	0.51	253
2000	4000	20	0.71	354	0.70	350	0.63	317	0.57	284	0.50	251	0.44	218
2200	4400	22	0.63	316	0.62	311	0.56	278	0.49	245	0.43	212	0.36	180
2400	4800	24	0.55	274	0.54	269	0.47	236	0.41	203	0.34	170	0.28	137
2600	5200	26	0.46	228	0.45	223	0.38	190	0.32	158	0.25	125	0.18	92
2700	5400	27	0.41	203	0.40	199	0.33	166	0.27	133	0.20	100	0.13	67
			$e_x/t_h = 0.05$										$e_x/t_h = 0.29$	

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 2.0$ applies to walls that have enhanced resistance to lateral movement at one end that have a free edge at the other end.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).

Table UL200-20-4

200 MORTARLESS WALL (UNCHAMFERED)

Block: 20 MPa
Grout: C25/30

Wall Span: HORIZONTAL
 Category 1 masonry units (refer BS 5628-1 Clause 3.3)

$a_h = 2.5$

			MAXIMUM DESIGN LOAD IN COMPRESSION (N_d) WITH DIFFERENT ECCENTRICITIES											
Wall Length L (mm)	$L_{ef} = 2.5 L$ (mm)	$S_r = L_{ef}/t$	$e_x = 8.7\text{mm}$		$e_x = 10\text{mm}$		$e_x = 20\text{mm}$		$e_x = 30\text{mm}$		$e_x = 40\text{mm}$		$e_x = 50\text{mm}$	
			β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)	β	N_d (kN/m)
600	1500	7.5	1.00	500	0.99	495	0.88	440	0.77	385	0.66	330	0.55	275
800	2000	10	0.98	492	0.98	487	0.88	440	0.77	385	0.66	330	0.55	275
1000	2500	12.5	0.93	466	0.92	461	0.88	440	0.77	385	0.66	330	0.55	275
1200	3000	15	0.87	434	0.86	430	0.79	397	0.77	385	0.66	330	0.55	275
1400	3500	17.5	0.79	397	0.79	393	0.72	360	0.65	327	0.59	294	0.52	261
1600	4000	20	0.71	354	0.70	350	0.63	317	0.57	284	0.50	251	0.44	218
1800	4500	22.5	0.61	305	0.60	301	0.54	268	0.47	235	0.40	202	0.34	169
2000	5000	25	0.50	251	0.49	247	0.43	214	0.36	181	0.30	148	0.23	115
2100	5250	26.25	0.44	222	0.44	217	0.37	185	0.30	152	0.24	119	0.17	86
			$e_x/t_b = 0.05$										$e_x/t_b = 0.29$	

NOTES:

Linear interpolation between all values in the table is permitted, but do not extrapolate.

a_h is the effective length multiplier. $a_h = 2.5$ applies to walls that have simple resistance to lateral movement at one end that have a free edge at the other end.

e_x is the effective eccentricity at the top of the wall. t is the thickness of the wall (= 200mm), and t_b is the equivalent bedded thickness of the wall (= 174mm)

Short walls:

When $S_r \leq 6$ and $e_x/t_b \leq 0.05$, walls can be designed for compression only (i.e. there is no need to design for bending).

When $S_r \leq 6$ and $0.05 < e_x/t_b \leq 0.5$, walls must be designed for combined bending and compression. This is accounted for when using the above table.

When $S_r \leq 6$ and $e_x/t_b > 0.5$, walls may be designed as a member in bending only, disregarding the vertical load.

Slender walls:

When $6 < S_r < 27$ the wall can be designed in the same manner as short walls but the design moment must be increased to account for lateral deflection of the wall panel. This is accounted for in the above table. (Note that BS 5628-2 classifies walls with $S_r > 12$ as slender walls, however the limit from BS 5628-1 has been adopted as this is more conservative, and as mortarless walls are designed as unreinforced in compression.)

Grout:

The minimum permissible grout strength (cube strength) is the unconfined compressive strength of the block, however the grout strength is not to be less than C25/30 (to BS 8500). Check also the requirements of BS 5628-2:2005 for exposure situations E1 to E4 and the requirements for minimum cement content (starts at 315 kg/m³) and minimum free w/c ratio (refer BS 5628-2:2005 Table 15).